

UPM Raflatac Technical Information

09-12-2020 EN SI

Product	RAFLACOAT OP NXT+FSC / PERM.GREENTAC + / KRAFT SPECIAL 83-FSC / SCORE PRINTED
Sales Code	GPG/SP34/EJB/W3
Product use	Product designed for mid-gloss labels with high opacity, for correcting erros and text changes. Recomened for block-out labels where total coverage is required. The RAFNXT+ product design results in a superior carbon performance by leveraging a smarter choice and use of materials.

Typical technical values

Face	RAFLACOAT OP NXT+FSC
Product	On machine coated woodfree SC paper, with grey reverse side to increase the opacity.
Substance	82 g/m ² ISO 536
Caliper	70 μm ISO 534
Tensile strength MD	5.8 kN/m ISO 1924/1
Tensile strength CD	2.8 kN/m ISO 1924/1
Brightness	75 % ISO 2470/1
Roughness	1 μm ISO 8791
Opacity	99 % ISO 2471
Gloss	64 % Hunter 75°
CIE Whiteness	106 % ISO 11475
Stiffness MD	0.23 mNm ISO/DP 2493
Stiffness CD	0.13 mNm ISO/DP 2493
Printability	Flexography, letterpress, screen, offset, thermal transfer.
Sustainability	The product is sold as FSC Mix Credit under UPM Raflatac's FSC™ certificate SGSCHCOC-004879.

Adhesive	SP34 GREENTAC PLUS
Type	General permanent adhesive for sheets.
Composition	Modified acrylic dispersion.
Tack min	10 N FTM 9
Shear min	2 h FTM 8

Backing	KRAFT SPECIAL 83-FSC
Product	White woodfree kraft backing paper
Substance	83 g/m ² ISO 536
Caliper	84 μm ISO 534
Tensile strength MD	8.7 kN/m ISO 1924
Tensile strength CD	3.8 kN/m ISO 1924



Sustainability

The product is sold as FSC Mix Credit under UPM Raflatac's FSC™ certificate SGSCHCOC-004879.

Performance

Total caliper	173 µm
Minimum labelling temperature	5 °C
Service temperature	- 10 to 100 °C
Shelf life	From date of manufacture: 48 months, under FINAT defined storage conditions (+20-25°C and 40-50% RH). Prolonged storage at higher temperatures and/or humidity levels will shorten the shelf life.

Information

Product Information

Scoring is crucial to ensuring self-adhesive labels are easily peeled away from their backing. Our sheets have folding scores that are spaced at 35 mm intervals, what enables a smooth label opening. Scores open after bending 90–120° Scores don't open if they have not been folded previously.

Approvals

Approvals

For further compliance information related to food labeling applications, please contact your local sales representative for a Declaration of Conformance (DoC) document.

Approvals

Toy labeling: This product complies with the European Standard EN71-3:2013 "Safety of Toys" - Migration of certain elements.

Disclaimer

The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.

