

UPM Raflatac Technical Information

11.09.2012 ENG 849

SELF-ADHESIVE	SHEETS
FACE	RAFLACOAT OPAQUE FMC
Opaque	CLY (sales code)
Product	On machine coated woodfree SC paper, with grey reverse side to increase the opacity.
Use	A multipurpose label paper; white gloss finish, gives accurate graphic results. Gloss can easily be increased by using UV-varnish.

Typical technical values

Substance	82	g/m ²	ISO 536	
Caliper	70	µm	ISO 534	
Tensile strength MD	5.8	kN/m	ISO 1924/1	
Tensile strength CD	2.8	kN/m	ISO 1924/1	
Brightness	75	%	ISO 2470/1	
Roughness	1.0	µm	ISO 8791	PPS 10
Opacity	99	%	ISO 2471	
Gloss	64	%	Hunter 75°	
Stiffness MD	0.23	mNm	ISO/DP 2493	
Stiffness CD	0.13	mNm	ISO/DP 2493	
Printability	Flexography, letterpress, screen, offset, thermal transfer.			
Sustainability	Products named as FMC are registered to SGS-COC-004879 FSC™ mixed credit.			
Warranty	Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. This publication replaces all previous versions. All information is subject to change without notice.			



UPM

www.upmraflatac.com